

# CPP Easy Peel for Lids

## New generation of CPP film Easy Peel for Lids



- Retort up to 121°C
- Very smooth opening
- No angelhair opening
- High transparency
- Available from 50 micron

Among its portfolio RC-Film suggests one CPP film, which is specifically developed for Easy Peel Lids. This film combines in itself all the specific technical requirements to perfectly satisfy the difficult care of Trays such as FruitBowls.

Very smooth opening, no angelhair and semi retort capabilities provide our customers the perfect solution for the Tray Easy Peel lids.

**RCP-05, RCP-06 is available in thickness from 50 micron up to 70 micron; for specific requests, please contact us.**

CHARACTERISTIC	TEST METHODOLOGY		UNIT	RCP-05	RCP-06
Thickness	DIN 53370	-	micron	50	50
Density	-	-	gr/cm <sup>3</sup>	0.82	0.82
Weight	-	-	gr/cm <sup>2</sup>	41	41
MFI	ASTM 1238	-	gr/10min	9.3	9.3
COF dynamic	ASTM D-1894	NT/NT	-	0.5	0.5
Corona Treatment	ASTM D-2578	-	dynes/cm <sup>2</sup>	38	38
Peel Strength	PET12/Alu7/cPP on PP tray	-	N/15mm	7	7
Elongation at Break	ASTM D-882	MD	%	650	650
		TD		700	700



*Values are based on a large number of test samples; values are indicative and do not represent the technical specification of the film.*

Amata City Industrial Estate; 7/451 Moo 6, Mabyangporn, Pluakdang, Rayong 21140 Thailand – Property Information.  
Tel: +66 (0) 38-913697-98, Fax: +66 (0) 38-913699, Email: [info@rc-film.com](mailto:info@rc-film.com) and [www.rc-film.com](http://www.rc-film.com)

